

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 514 720 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **92107773.1**

(22) Date of filing: **08.05.92**

(51) Int. Cl.⁵: **A61K 37/02, //(A61K37/02, 31:565), (A61K37/02, 31:66), (A61K37/02, 31:135), (A61K37/02, 33:16)**

(30) Priority: **03.05.91 US 695310**

(43) Date of publication of application:
25.11.92 Bulletin 92/48

(84) Designated Contracting States:
**AT BE CH DE DK ES FR GB GR IT LI LU MC
NL PT SE**

(71) Applicant: **CELTRIX PHARMACEUTICALS, INC.**
3055 Patrick Henry Drive
Santa Clara, CA 95052-8203(US)

(72) Inventor: **Adams, Steven W.**
1201 Heatherstone Way
Sunnyvale, California 94087(US)
Inventor: **Armstrong, Rosa**
2130 Mass Avenue
Cambridge, Massachusetts 02140(US)
Inventor: **Rosen, David**
3141 Valmalne Court
San Jose, California 95135(US)

(74) Representative: **Goldin, Douglas Michael et al**
J.A. KEMP & CO. 14, South Square Gray's Inn
London WC1R 5LX(GB)

(54) **Bone growth factors and inhibitors of bone resorption for promoting bone formation.**

(57) Bone growth factors are used to stimulate new bone formation when administered with agents that inhibit bone resorption. These therapeutic combinations result in an enhanced rate of bone formation with an increase in bone mass.

EP 0 514 720 A2

Field of the Invention

The instant invention relates generally to polypeptide factors and their use in bone growth and maturation. Specifically, the invention relates to the use of bone growth factors to stimulate new bone formation when used with agents that inhibit bone resorption. These therapeutic combinations result in an enhanced rate of bone formation with an increase in bone mass.

Background of the Invention

The transforming growth factor beta (TGF- β) family has been implicated in a variety of physiological processes involving bone *in vivo* and *in vitro*. For example, *in vitro* studies, TGF- β stimulates proliferation and matrix synthesis of osteoblastic cells (Centrella, et al. (1987) *J. Biol. Chem.* 262:2869-2874) and has been reported to inhibit the formation and activity of osteoclastic cells (Chenu, et al. (1988) *Proc. Natl. Acad. Sci. U.S.A.* 85:683-687; Oreffo, et al. (1988) *J. Bone Min. Res.* 3:439-446). *In vivo*, subperiosteal injections of TGF- β in the femur (Joyce, et al. (1990) *J. Cell. Biol.* 110:2195-2207) and calvarium (Noda and Camilliere (1989) *Endocrinology* 124:2991-2294) of rodents stimulate local bone formation. Furthermore, mice injected daily subcutaneously with TGF- β showed an increase in the number of cuboidal osteoblasts along with increased deposition of bone matrix, while rats similarly treated showed an increase in osteoblasts, demonstrating the systemic *in vivo* activity of TGF- β on bone (Mathews, et al. "Systemic delivery of TGF- β produces a marked increase in osteoblasts, stimulates osteoid synthesis and increases bone formation rates in long bones and vertebrae in rats," poster presented at the 1990 Meeting of the American Society of Bone and Mineral Research).

Activins are dimeric proteins structurally similar to inhibin, TGF- β 1, TGF- β 2, and other proteins that makeup a family of proteins structurally related to TGF- β 1. These proteins exhibit the chromatographic properties of TGF- β s. In addition to having homology with respect to the amino acid sequences, activins exhibit conservation of cysteine positions characteristic of the TGF- β s. Activins exhibit a molecular weight of 25 kD under nonreducing conditions by SDS-PAGE (and a molecular weight of 14 kD under reducing conditions). There are two known forms of the activin subunits, which have been termed β A or β B. Homodimeric forms β AA and β BB and a heterodimeric form β AB have been described in the literature. Activin subunits have about a 30% homology to TGF- β 1 and TGF- β 2 chains in terms of their amino acid sequences. Inhibins are polypeptides which are also structur-

ally related to activins. Inhibins are heterodimers of the activin β A or β B subunit and a separate α subunit. Inhibins exhibit activity essentially opposite to activin.

The activin β A homodimer and β AB heterodimer have been purified from porcine follicular fluid, and have been shown to stimulate the release of follicle stimulating hormone (FSH) from rat pituitary cells *in vitro* (W. Vale et al., *Nature* - (1986) 321:776-79). Other reported activities include stimulation of oxytocin release from neurosecretory neurons (P.E. Sawchemko, et al., *Nature* (1988) 334:615-17; W. Vale et al., "Recent Progress in Hormone Research" (1988) 44:1-34); stimulation of insulin secretion from pancreatic islets (Y. Totsuka et al., *Biochem. & Biophys. Res. Comm.* (1988) 156:335-39); and stimulation of erythroid and multi-potential progenitor cell colony formation in bone marrow culture (J. Yu et al., *Nature* (1987) 330:765-67; H.E. Broxmeyer et al., *Proc. Natl. Acad. Sci. U.S.A.* (1988) 85:9052-56). Activin β A is apparently identical to erythroid differentiation factor (EDF) (M. Murata et al., *Proc. Natl. Acad. Sci. U.S.A.* (1988) 85:2434-38).

Despite the fact that activin is similar in amino acid sequence to TGF- β , activin does not compete with TGF- β for binding to TGF- β receptors types I, II, or III present on fibroblasts and epithelial cells. However, activin has been reported to compete against binding of TGF- β 1 to rat pituitary tumor cells (S. Cheifetz et al., *J. Biol. Chem.* (1988) 263:17225-28). TGF- β 1 and TGF- β 2 have been reported to induce formation of endochondral bone *in vivo* (M.E. Joyce et al., *J. Cell Biol.* (1990) 110:2195-2207).

A "bone morphogenetic protein" (BMP) was extracted from demineralized bone using urea or guanidine hydrochloride and reprecipitated according to the disclosures in U.S. Patent Nos. 4,294,753 and 4,455,256 to Urist. Urist subsequently reported (Urist, M. R., *Clin. Orthop. Rel. Res.* (1982) 162:219) that ion exchange purification of this crude protein mixture yielded an activity which was unadsorbed to carboxymethyl cellulose resin (CMC) at pH 4.8. Urist's reports in *Science* (1983) 220:680-685 and *Proc. Natl. Acad. Sci. U.S.A.* - (1984) 81:371-375 describe BMPs having molecular weights of 17,500 and 18,500 daltons. Urist's patent publication, EPA Publication No. 0212474, describes BMP fragments of 4,000 to 7,000 daltons obtained by limited proteolysis of BMP.

U.S. Patent No. 4,608,199 describes a bone-derived protein of 30,000-32,000 daltons. The protein is described as being water soluble and having no affinity for concanavalin A.

WO 88/00205 reports four proteins, designated BMP-1, BMP-2 Class I ("BMP-2"), BMP-3, and BMP-2 Class II ("BMP-4"), that are alleged to have

osteogenic activity.

J.M. Wozney, in *Growth Factor Research*, Vol. 1 (1989), pp. 267-280, describes three additional BMP proteins closely related to BMP-2, and which have been designated BMP-5, BMP-6 and BMP-7.

WO 89/09787 and 89/09788 describe a protein called "OP-1", now known to be BMP-7. The cloning of BMP-7 is described in E. Ozkaynak et al., *EMBO Journal* (1990) 9:2085-2093, and the purification of BMP-7 is described in T.K. Sampath et al., *J. Biol. Chem.* (1990) 265:13198-13205.

U.S. Patent No. 4,434,094 to Seyedin and Thomas reported the partial purification of a bone generation-stimulating, bone-derived protein by extraction with chaotropic agents, fractionation on anion and cation exchange columns, and recovery of the activity from a fraction adsorbed to CMC at pH 4.8. This new protein fraction was termed "osteogenic factor" and was characterized as having a molecular weight below about 30,000 daltons.

Isgaard, et al. (*Endocrinol. Metab.* 13:E367-72,1986) reports the stimulation of bone growth by insulin-like growth factor (IGF).

Slovik et al. (*J. Bone & Min. Res.* 1:377-381, 1986) report the stimulation of bone growth by parathyroid hormone (PTH).

In vitro evidence suggests resorption of bone and formation of new bone appear to be coupled in some fashion. TGF- β , for example, is apparently involved in this process. Pfeilschifter and Mundy, *Proc. Natl. Acad. Sci. U.S.A.* (1987) 84:2024-2028, demonstrated that calvariae incubated with parathyroid hormone, 1,25-dihydroxyvitamin D₃, and interleukin 1, all factors that stimulate bone resorption, showed an increase in endogenous TGF- β activity in the culture medium, whereas incubation with calcitonin, which inhibits bone resorption, correlated with a decrease in endogenous TGF- β activity.

The present invention offers in vivo combination therapy for stimulating new bone formation through the combined administration of an exogenous bone growth factor and an agent which inhibits bone resorption. These combinations provide more effective therapy for prevention of bone loss and replacement of bone than the components alone, as the combination appears to synergistically enhance the increase in bone mass and the rate of bone formation.

Summary of the Invention

The present invention includes a method for stimulating new bone formation in a subject by administration of the combination of a bone growth factor and an inhibitor of bone resorption. Preferably, the bone growth factor is TGF- β , activin, BMP, IGF, PTH, or active fragments thereof, and

the inhibitor of bone resorption is an estrogen, bisphosphonate, sodium fluoride, calcitonin, or tamoxifen, or related compounds.

Another aspect of the invention is a method for treating bone loss in a subject by administration of the combination of a bone growth factor and an inhibitor of bone resorption.

The invention further provides for a composition of a bone growth factor and an inhibitor of bone resorption for inducing bone formation in a subject.

Another aspect of the invention is a composition of a bone growth factor and an inhibitor of bone resorption for treatment of bone loss in a subject.

Brief Description of the Drawings

Figures 1A and 1B are photomicrographs depicting the double fluorochrome labeling of trabecular surfaces in ovariectomized rats (A) and ovariectomized rats treated with estrogen (B).

Figures 2A and B are photomicrographs depicting the double fluorochrome labeling of trabecular surfaces in ovariectomized rats receiving TGF- β (A) or TGF- β and estrogen (B).

Figure 3 is a graph comparing the ratio of organic to inorganic content of bone from ovariectomized rats and ovariectomized rats treated with estrogen.

Figure 4 is a graph comparing the ratio of organic to inorganic content of bone from ovariectomized rats and ovariectomized rats treated with TGF- β and TGF- β plus estrogen.

Figure 5A is a graph comparing the percent of double-labelled bone surface in ovariectomized rats treated with TGF- β , estrogen, TGF- β + estrogen, or vehicle alone. Figure 5B is a graph comparing the rate of bone formation in ovariectomized rats treated with TGF- β , estrogen, TGF- β + estrogen, or vehicle alone.

Detailed Description of the Invention

A. Definitions

It must be noted that as used in this specification and the appended claims, the singular forms "a", "an" and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "a TGF- β " includes statistical mixtures of dimeric proteins of the type generally described herein; and reference to "the method of administration" includes one or more methods of the type described herein and/or of the type which will become apparent to those of ordinary skill in the art upon reading this disclosure.

The term "bone growth factor" refers to the

families of proteins which affect bone or cartilage formation. Examples of bone growth factors include transforming growth factor-beta (TGF- β), activin, IGF, PTH, and bone morphogenic factor (BMP).

The term "TGF- β " refers to beta-type transforming growth factors, including TGF- β 1, TGF- β 2, TGF- β 3, TGF- β 4, TGF- β 5, heterodimers of the TGF- β polypeptide chains (e.g. TGF- β 1.2), and fragments thereof, synthetic peptides, and homologous proteins having substantially equivalent biological activity in any of the numerous known TGF- β assays, such as the one described in Methods for Preparation of Media, Supplements, and Substrate for Serum-free Animal Cell Culture (1984) pp. 181-194. Alan R. Liss, Inc. This particular assay determines ability to induce anchorage-dependent growth in non-neoplastic normal rat kidney (NRK) fibroblasts by measuring the formation of cell colonies in soft agar. Other known TGF- β activity assays include but are not limited to stimulation of osteoblast proliferation, inhibition of keratinocyte proliferation, stimulation of collagen synthesis in a variety of cells, inhibition of mitogen-stimulated T-cell proliferation, and stimulation of chemotactic activity. Preparation of TGF- β 1 and TGF- β 2 is described in U.S. Pat. No. 4,774,322, incorporated herein by reference. Additional TGF- β s have also been described. U.S. Patent No. 4,886,747 describes the identification of TGF- β 3 and its nucleotide sequence, and describes a method for recovery of TGF- β from recombinant cell cultures. S. B. Jakowlew et al., Molec. Endocrinol. (1988) 2:1186-1195, describes TGF- β 4 and its nucleotide sequence, identified by cDNA characterization. A.B. Roberts et al., Growth Factors, Vol. 2 (1990) pp. 135-147, describes the purification of TGF- β 5 from Xenopus-conditioned medium.

The term "TGF- β " as used herein is also intended to include the heterodimer TGF- β 2.3, disclosed in copending patent application U.S. Ser. No. 614,306, filed 11/16/90. TGF- β 2.3 may be prepared from an extract of bone by pooling side fractions from peaks of column chromatography, subjecting those fractions to reverse phase HPLC and recovering those fraction which migrate more slowly than TGF- β 2 by SDS-PAGE, subjecting those slower migrating fractions to FPLC and recovering those that migrate during a pH 4.6 to 6.7 gradient, subjecting the pH 4.6 to 6.7 eluant to reverse phase HPLC or gel electrophoresis, and recovering substantially pure TGF- β 2.3.

The term "TGF- β " as used herein is also intended to include any other synthetic molecule whose mechanism of action is mediated through the TGF- β receptor or second messenger pathway.

Because these proteins are non-species-specific in their activity they may be used to treat

subjects in general, including sport, pet, and farm animals, and humans.

The term "inhibition of bone resorption" refers to prevention of bone loss, especially the inhibition of removal of existing bone either from the mineral phase and/or the organic matrix phase, through direct or indirect alteration of osteoclast formation or metabolism. Thus, the term "inhibitor of bone resorption" as used herein refers to agents that prevent bone loss by the direct or indirect alteration of osteoclast formation or metabolism.

The term "osteogenically effective" means that amount which effects the formation and differentiation of mature bone. As used herein, an osteogenically effective dose is also "pharmaceutically effective."

The term "subject" as used herein refers to a living vertebrate animal such as a mammal or bird in need of treatment, i.e., in need of bone repair or replacement. Such need arises locally in cases of bone fracture, nonunion, defect, prosthesis implantation, and the like. Such need also arises in cases of systemic bone disease, as in osteoporosis, osteoarthritis, Paget's disease, osteomalacia, osteomalacia, multiple myeloma and other forms of cancer, and age-related loss of bone mass.

The term "treatment" as used herein shall mean (1) providing a subject with an amount of a substance sufficient to act prophylactically to prevent the development of a weakened and/or unhealthy state; or (2) providing a subject with a sufficient amount of a substance so as to alleviate or eliminate disease state and/or the symptoms of a disease state, and a weakened and/or unhealthy state.

B. General methods

Drugs which prevent bone loss and/or add back lost bone may be evaluated in the ovariectomized rat. This animal model is well established in the art (see, for example, Wronski, et al. (1985) Calcif. Tissue Int. 37:324-328; Kimmel, et al. (1990) Calcif. Tissue Int. 46:101-110; and Durbridge, et al. (1990) Calcif. Tissue Int. 47:383-387; these references are hereby incorporated in their entirety). Wronski, et al. ((1985) Calcif. Tissue Int. 43:179-183)) describe the association of bone loss and bone turnover in the ovariectomized rat.

Examples of inhibitors of bone resorption include estrogens, bisphosphonates, calcitonins, sodium fluorides, and tamoxifens (Turner, et al. (1987) J. Bone Mineral Res. 2:115-122; Wronski, et al. (1988) Endocrinology 128:681-686; and Wronski, et al. (1989) Endocrinology 125:810-816; Pfeilshifter, et al. (1987) Proc. Natl. Acad. Sci. U.S.A. 84:2024-2028; Turner, et al. (1988) Endocrinology

122:1146-1150). The entire molecule of a particular inhibitor may be used, or alternatively, only a functional part of the inhibitor molecule may be used.

Pharmaceutical formulations of the invention which include a bone growth factor and/or an inhibitor of bone resorption for administration will generally include an osteogenically effective amount of the bone growth factor to promote bone growth, in addition to a pharmaceutically acceptable excipient. Suitable excipients include most carriers approved for parenteral administration, including water, saline, Ringer's solution, Hank's solution, and solutions of glucose, lactose, dextrose, ethanol, glycerol, albumin, and the like. These compositions may optionally include stabilizers, antioxidants, antimicrobials, preservatives, buffering agents, surfactants, and other accessory additives. The TGF- β and inhibitor of bone resorption may also be delivered in a slow release form from a suitable carrier.

A presently preferred vehicle comprises about 1 mg/ml serum albumin (species-specific) in phosphate-buffered saline (PBS) or isotonic citrate buffer. A thorough discussion of suitable vehicles for parenteral administration may be found in E.W. Martin, "Remington's Pharmaceutical Sciences" (Mack Pub. Co., current edition sections relating to the excipient vehicles and formulating being incorporated herein by reference to disclose such). Such formulations are generally known to those skilled in the art and are administered systemically to provide systemic treatment.

A bone growth factor and an agent which inhibits bone resorption may be administered sequentially or simultaneously as a single composition to the subject. If administered sequentially, the period between the administration of the bone growth factor and the inhibitor of bone resorption will typically be one week to one year, and optimally, one week to six months.

If the bone growth factor and the agent which inhibits bone resorption are administered as a single composition, the molar ratio of bone growth factor to inhibitor of bone resorption will be about 10:1 to 1:10, preferably, 5:1 to 1:5, and optimally, 1:1. The optimal ratio is expected to vary from compound to compound. Furthermore, if administered as a single composition, the bone growth factor and the inhibitor of bone resorption may be separate components of the composition, or they may be conjugated to each other.

The precise dosage necessary will vary with the age, size, sex and condition of the subject, the nature and severity of the disorder to be treated, and the like; thus, a precise effective amount cannot be specified in advance and will be determined by the caregiver. However, appropriate amounts may be determined by routine experimentation with

animal models, as described below. In general terms, an effective dose of a bone growth factor for systemic treatment will range from about 0.001 μ g/kg to about 10 mg/kg of body weight. An effective dose for estrogen is about 1 μ g/kg to about 1 mg/kg of body weight. An effective dose for bisphosphonates is about 0.05 μ g/kg to about 15 mg/kg of body weight. An effective dose for calcitonin is about 0.05 MRCU (Medical Research Council Units)/kg to about 2.5 MRCU/kg of body weight.

Effective doses for local administration would be about 0.001 μ g to 1 mg per application site.

The methods and compositions of the invention are useful for treating bone fractures, defects, and disorders which result in weakened bones such as osteoporosis, osteoarthritis, Paget's disease, osteomalacia, bone loss resulting from multiple myeloma and other forms of cancer, bone loss resulting from side effects of other medical treatment (such as steroids), and age-related loss of bone mass.

In accordance with one method of use, the bone growth factor and the inhibitor of bone resorption may be administered systemically either orally and/or parenterally, including subcutaneous or intravenous injection, and/or intranasally. Additionally, the bone growth factor and the inhibitor of bone resorption may be delivered in a slow release form from a suitable carrier.

In accordance with another method of use, the bone growth factor may be administered locally to a specific area in need of bone growth or repair, with either the concomitant administration of the inhibitor of bone resorption at the site, or the administration of the inhibitor of bone resorption in a separate vehicle, or, the inhibitor of bone resorption may be provided locally, with the administration of the bone growth factor in a separate vehicle. Thus, the bone growth factor and/or inhibitor of bone resorption may be implanted directly at the site to be treated, for example, by injection or surgical implantation in a sustained-release carrier. Suitable carriers include hydrogels, controlled- or sustained-release devices (e.g., an Alzet® minipump), polylactic acid, and collagen matrices. Presently preferred carriers are formulations of atelopeptide collagen containing particulate calcium phosphate mineral components, such as combinations of homologous or xenographic fibrillar atelopeptide collagen (for example Zyderm® Collagen Implant, available from Collagen Corporation, Palo Alto, California) with hydroxyapatite/tetracalcium phosphate (HA-TCP, available from Zimmer, Inc., Warsaw, IN). It is presently preferred to administer implant compositions containing a bone growth factor and/or an inhibitor of bone resorption in a collagen/mineral mixture implant.

Bone growth factors and/or an inhibitor of bone resorption, delivered in sustained-release vehicles is also particularly useful for improving implant fixation, for example for improving ingrowth of new bone into a metal prosthesis in joint reconstruction and dental or orthopedic implants. Alternatively, the bone growth factor may be delivered in the implant, with the inhibitor delivered in a separate vehicle, and vice-versa.

Dental and orthopedic implants can be coated with bone growth factors in combination with an inhibitor of bone resorption, to enhance attachment of the implant device to the bone. Alternatively, the bone growth factor can be used to coat the implant, and the inhibitor of bone resorption can be administered concomitantly or sequentially in a separate vehicle, and vice-versa.

In general, implant devices may be coated with a bone growth factor and/or an inhibitor of bone resorption as follows. The bone growth factor (and the inhibitor of bone resorption, if desired) is dissolved at a concentration in the range of 0.01 $\mu\text{g/ml}$ to 200 mg/ml in phosphate-buffered saline (PBS) containing 2 mg/ml serum albumin. The porous end of an implant is dipped in the solution and is airdried (or lyophilized) or implanted immediately into the bony site. The viscosity of the coating solution is increased, if desired, by adding hyaluronate at a final concentration of 0.1 mg/ml to 100 mg/ml or by adding other pharmaceutically acceptable excipients. Alternatively, the solution containing the bone growth factor (and the inhibitor of bone resorption, if desired) is mixed with collagen gel or human collagen (e.g. Zyderm® Collagen Implant, Collagen Corp., Palo Alto, CA) to a final collagen concentration of 2 mg/ml to 100 mg/ml to form a paste or gel, which is then used to coat the porous end of the implant device. The coated implant device is placed into the bony site immediately or is airdried and rehydrated with PBS prior to implanting, with the objective of maximizing new bone formation into the implant while minimizing the ingrowth of soft tissue into the implant site.

C. Examples

The following examples are put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how to extract, isolate, formulate and use the compositions and methods of the invention and are not intended to limit the scope of what the inventors regard as their invention. Efforts have been made to insure accuracy with respect to numbers used (e.g., amounts, times, temperature, etc.), but some experimental error and deviations should be accounted for. Unless indicated otherwise, parts are parts by weight, temperature is in degrees centigrade,

pressure is at or near atmospheric, and other parameters are conventional and in accordance with those normally accepted by those skilled in the art.

Example 1

Twenty-five day old Sprague-Dawley rats were either ovariectomized (OVX) or sham operated and housed to allow bone loss for eight weeks. Five ovariectomized and three sham operated rats received 5 μg TGF- β 2 subcutaneously daily for 7 days. Four ovariectomized rats received vehicle only daily for 7 days. Rats were euthanized at the end of 7 days treatment and femurs were dissected from soft tissue.

Bone specimens were fixed in ethanol, processed and embedded undecalcified in methylmethacrylate. Thin sections (4 μm) of the distal femur were cut on a Reichert-Jung microtome. Thin sections were stained with toluidine blue for general morphology.

Qualitative evaluation was performed on femurs from rats in the above groups. Both trabecular bone and cortical endosteal surfaces in the sham controls were generally quiescent (i.e. little osteoblastic or osteoclastic activity). By contrast, in the sham plus TGF- β treatment group, osteoblasts and osteoclasts were more easily recognized than either the sham controls or either OVX group.

Thus, these observations provide evidence of increased bone turnover in sham operated animals when treated with TGF- β compared with non-treated sham operated rats. Since the same extent of bone turnover was not seen in ovariectomized rats treated with TGF- β compared with vehicle-treated ovariectomized controls, it appears that intact animals possess a factor(s) that allows TGF- β to stimulate new bone formation that is absent in the ovariectomized animal.

Example 2

Forty two Sprague-Dawley rats, 90 days old, were ovariectomized and housed to allow bone loss for 10 weeks after surgery. At 70 days post-surgery, rats were treated daily with TGF- β 2 at 5 $\mu\text{g}/\text{animal}$ with or without 17 β -estradiol at 10 $\mu\text{g}/\text{kg}$ (5 days/week) for 2 weeks. Additional groups of ovariectomized rats were treated with vehicle alone or 17 β -estradiol alone as a control. Each group consisted of 6 rats.

Bone was metabolically labeled with fluorochrome markers, calcein, and tetracycline. Calcein was given 7 days before euthanasia and tetracycline 2 days before euthanasia to allow evaluation of rate of mineralization and bone formation.

The first lumbar vertebra and tibias were cleaned of all adhering soft issue and defatted in

acetone for 2 days at room temperature. After drying for 1 hour, bones were further dried for 2 days in an oven at 80°C, cooled for one hour, and weighed on an analytical balance. The bones were then ashed in a muffle furnace for 2 hours at 600°C and cooled for 45 minutes in a desiccator. The bone samples were charred on a hot plate during addition of 2NHNO₃, and final charring done over an open flame. The samples were then ashed for 24 hours in a muffle furnace at 600°C, cooled for 45 minutes in a desiccator, and weighed again to obtain the ash/dry weight of bone.

Bone specimens for histology were dehydrated in ethanol and embedded undecalcified in methylmethacrylate. Thin sections (4µm) and thick sections (15µm) of the distal femur were cut on a Reichert-Jung 2050 microtome. Thin sections were stained with toluidine blue to evaluate general morphology and deposition of osteoid. Thick sections were left unstained to assess the dynamic parameters of bone turnover indicated by the fluorochrome markers.

Measurements of dry weights and ash weights were used to calculate a ratio of organic to inorganic content of both the tibia and the first lumbar vertebra. The results are shown in Figures 3 and 4.

As demonstrated in Figure 3, treatment with estrogen alone resulted in a slight decrease in the organic/inorganic ratio of tibias when compared to non-treated OVX controls, and TGF-β₂ at 5 µg/animal resulted in a small increase in the organic/inorganic ratio. However, when TGF-β₂ was administered with 17β-estradiol the organic/inorganic ratio was far greater than with either agent alone, and was significantly greater than the non-treated OVX control.

A similar result was seen when evaluating the vertebrae L1 as shown in Figure 4. A decrease in the organic/inorganic ratio was seen with estrogen alone. In this site, no increase in organic/inorganic ratio was seen with treatment with TGF-β alone, although treatment with TGF-β plus 17β-estradiol resulted in a significant increase in the organic/inorganic ratio when compared with non-treated OVX controls.

Examination of stained sections indicated that non-treated OVX control animals and rats treated with estrogen had very small amounts of osteoid deposition on trabecular surfaces. In contrast, rats treated with TGF-β had significant increases in the total amount of stainable osteoid. Rats that had received both TGF-β and estrogen had even larger amounts of osteoid deposition than with either factor alone.

Qualitative examination of unstained sections indicated that non-treated OVX rats and rats treated with estrogen had small amounts of trabecular sur-

face containing double fluorochrome labels (Figures 1A and 1B; 15 µm sections viewed with a fluorescence microscope at a magnification of 40X; b denotes bone; m denotes bone marrow; double-labeled surface are indicated by arrows). Rats treated with TGF-β had increased amounts of double-labeled trabecular surface, compared to the previous two groups, while those that had received TGF-β and estrogen showed the highest levels of double labeled surfaces of all experimental groups. This correlated well with the increases in deposition of osteoid and the wider osteoid seams described above.

The histomorphometric data were collected in the epiphyseal spongiosa of femurs. One row of fields was measured at 250X from cortex to cortex, and usually 10-14 fields were measured in each section. The corticoendosteal surfaces were not included in the measurements. Total perimeter (surface) and area (volume) of trabecular bone (Perimeter (mm) /Area (mm²) = bone volume) were traced onto a graphics tablet interfaced with a Macintosh computer. The percent of total trabecular surface covered by a single label (sLS) or a double label (dLS) was traced to calculate the per cent mineralising surface (MS) by the formula,

$$\%MS = (dLS + sLS/2)$$

BS

where BS denotes bone surface. Mineral appositional rates (MAR) were obtained by dividing the interlabel width by the interlabel time in days and correcting for the section obliquity to yield the corrected MAR in µm/day (Multiplied by 0.365 to convert to µg/yr). Bone formation rates (BFR) were computed conservatively using dLS only rather than the total MS as follows:

$$dLS \times \text{corr.MAR/BV} = \text{BFR.}$$

Data were expressed as a mean ± SP, and comparisons among groups were made using one factor ANOVAS. These data are shown in Figures 5A and 5B, where Figure 5A depicts the synergistic effect of TGF-β and estrogen in ovariectomized rats, and Figure 5B depicts the synergistic rate of bone formation in ovariectomized rats treated with TGF-β and estrogen.

Thus, the treatment of the ovariectomized rat with TGF-β resulted in increased bone formation rates. This increase, however, was significantly enhanced by concomitant treatment with estrogen.

Claims

1. A pharmaceutical composition comprising a bone growth factor and an inhibitor of bone resorption in a pharmaceutically acceptable excipient. 5
2. A composition according to claim 1, wherein the bone growth factor is TGF- β .
3. A composition according to claim 1, wherein the bone growth factor is an activin. 10
4. A composition according to claim 1, wherein the bone growth factor is a bone morphogenic protein (BMP). 15
5. A composition according to claim 1, wherein the bone growth factor is an IGF.
6. A composition according to claim 1, wherein the bone growth factor is parathyroid hormone (PTH). 20
7. A composition according to any one of claims 1 to 6, wherein the inhibitor of bone resorption is an estrogen. 25
8. A composition according to any one of claims 1 to 6, wherein the inhibitor of bone resorption is a calcitonin. 30
9. A composition according to any one of claims 1 to 6, wherein the inhibitor of bone resorption is a bisphosphonate. 35
10. A composition according to any one of claims 1 to 6, wherein the inhibitor of bone resorption is sodium fluoride.
11. A composition according to any one of claims 1 to 6, wherein the inhibitor of bone resorption is a tamoxifen. 40
12. A composition according to any one of the preceding claims, wherein the molar ratio of bone growth protein to inhibitor of bone resorption is 10:1 to 1:10. 45
13. A composition according to claim 12, wherein the molar ratio of bone growth protein to inhibitor of bone resorption is 5:1 to 1:1. 50
14. A composition according to any one of the preceding claims wherein the bone growth protein is conjugated to the inhibitor of bone resorption. 55
15. A composition according to any one of the preceding claims, further comprising a sustained-release vehicle.
16. A composition as defined in any one of claims 1 to 15 for use in a method of treatment of a human or animal subject for inducing bone formation.
17. A composition as defined in any one of claims 1 to 15 for use in a method of treatment of a human or animal subject for treating bone loss.
18. A composition according to claim 16 or 17 wherein the bone growth factor and the inhibitor of bone resorption are administered sequentially.
19. A composition according to claim 16 or 17 wherein the bone growth factor and the inhibitor of bone resorption are administered simultaneously.
20. A composition according to any one of claims 16 to 19 wherein the bone loss is osteoporosis-related, or osteomalacia-related or age related or is related to steroid therapy or is osteoarthritis-related or is related to Paget's disease or to cancer eg. multiple myeloma or wherein treatment is prophylactic.




FIG. 1A



FIG. 1B




FIG.2A



FIG.2B




FIG. 3




FIG. 4

FIG. 5A





FIG. 5B

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 514 720 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **92107773.1**

(22) Date of filing: **08.05.92**

(51) Int. Cl.⁵: **A61K 37/02, //(A61K37/02, 31:565), (A61K37/02, 31:66), (A61K37/02, 31:135), (A61K37/02, 33:16)**

(30) Priority: **03.05.91 US 695310**

(43) Date of publication of application:
25.11.92 Bulletin 92/48

(64) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IT LI LU MC NL PT SE

(68) Date of deferred publication of the search report:
03.03.93 Bulletin 93/09

(71) Applicant: **CELTRIX PHARMACEUTICALS, INC.**
3055 Patrick Henry Drive
Santa Clara, CA 95052-8203(US)

(72) Inventor: **Adams, Steven W.**
1201 Heatherstone Way
Sunnyvale, California 94087(US)
Inventor: **Armstrong, Rosa**
2130 Mass Avenue
Cambridge, Massachusetts 02140(US)
Inventor: **Rosen, David**
3141 Valmalne Court
San Jose, California 95135(US)

(74) Representative: **Goldin, Douglas Michael et al**
J.A. KEMP & CO. 14, South Square Gray's Inn
London WC1R 5LX (GB)

(54) **Bone growth factors and inhibitors of bone resorption for promoting bone formation.**

(57) Bone growth factors are used to stimulate new bone formation when administered with agents that inhibit bone resorption. These therapeutic combinations result in an enhanced rate of bone formation with an increase in bone mass.

EP 0 514 720 A3



DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
Y	EP-A-0 375 127 (GENENTECH) 27 June 1990 * column 5, line 41 - line 51 * * column 14, line 11 - line 14; claims * ---	1-20	A61K37/02 //(A61K37/02,31:565)(37/02,31:66)
X,Y	CHEMICAL ABSTRACTS, vol. 112, no. 12, 1988, Columbus, Ohio, US; abstract no. 104890, OTANI S. ET AL. 'Bone implant materials having porous carbon on surface and cell multiplication-accelerating layer.' * abstract * & JP-A-63 125 260 (RESEARCH AND DEVELOPMENT CORP.) 28 May 1988 ---	1-20	
X	CHEMICAL ABSTRACTS, vol. 109, no. 17, 1988, Columbus, Ohio, US; abstract no. 146842, & METAB., CLIN. EXP., vol. 37, no. 10, 1988, page 988-995 J. FARLEY ET AL. 'Evidence that fluorid-stimulated (3H) -thymidine incorporation in embryonic chick calvarial cell cultures is dependent on the presence of a bone cell mitogen, sensitive to changes in the phosphate concentration, and modulated by systemic skeletal effectors.' ---	1-20	TECHNICAL FIELDS SEARCHED (Int. Cl.5) A61K
X	EP-A-0 318 184 (SCHERING CORPORATION) 31 May 1989 * claims 1,12,13,14 * ---	1-20	
X	EP-A-0 272 890 (ELI LILLY AND COMPANY) 29 June 1988 * page 1, line 6 - line 22; claims * --- -/--	1-6,7, 15-20	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 DECEMBER 1992	Examiner BERTE M.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			

**Application Number**

EP 92 10 7773
Page 2

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
T	MEDLINE AN=90272939 KARLSRUHE & PUBLIC HEALTH REP. vol. 104, September 1989, pages 75 - 77 CC. JOHNSTON JR. 'Treatment of osteoporotic patients.' *Abstract* ---	1-20	
P,X	MEDLINE AN=92163668 KARLSRUHE & OSTEOPROS INT. vol. 2, no. 1, October 1991, ENGLAND U.K. pages 12 - 19 TURNER CH. 'Toward a cure for osteoporosis: reversal of excessive bone fragility.' ---	1-20	
P,X	EP-A-0 436 469 (CIBA-GEIGY) 10 July 1991 * claims 1,3,8,9,10 * -----	1-20	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
Place of search THE HAGUE		Date of completion of the search 18 DECEMBER 1992	Examiner BERTE M.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)